

Technical data - NYROSTEN N 113 FS

The technical data are not specifications. They represent mean values and do not guarantee specific characteristics.

NYROSTEN N 113 FS

CHARACTERISTIC	TEST STANDARD	VALUE
Color		goldish green after application
Flash point	DIN EN 22719/1	> 65 °C
Consistency		fluid
Solvent content		50 %
Processing		spraying, brushing

CHARACTERISTICS AFTER THE SOLVENT EVAPORATES

CHARACTERISTIC	TEST STANDARD	VALUE
Consistency		solid-elastic
Drop point	ISO 2176	
Drop point	DIN 51801/2	> 90 °C
Penetration	ISO 2137	40 - 70 1/10 mm
Flash point	DIN ISO 2592	> 220 °C
Breaking point (Application thickness 75 g/m ²)	DIN 52012	-30 °C

INITIAL ANTI-CORROSION PROTECTION

NYROSTEN N 113

SPECIAL FEATURES

Strongly bonding, outstanding anti-corrosion protection

DELIVERY OPTIONS

500 ML AEROSOL CAN 5 KG CAN 10 KG PAIL 25 KG HOBBOCK 200 KG BARREL

